

Desmopan 9370AU

/

Extrusion- and injection molding grade; with special UV stabilizers; very good hydrolysis and microbial resistance; good low-temperature flexibility; free from plasticizers; high moisture vapor transmission rate; Application; breathable films; Films; Sports shoe soles; hard - soft systems

ISO Shortname

Property	Test Condition	Unit	Standard	typical Value	
				drying	annealed - according to specifications
Mechanical properties (23 °C/50 % r. h.)					
C shore hardness A	1s	-	DIN ISO 7619-1		70
Ultimate tensile strength	200 mm/min	MPa	DIN 53504		26,8
Strain at break	200 mm/min	%	DIN 53504		794
Stress at 100 % strain	200 mm/min	MPa	DIN 53504		2,9
Stress at 300 % strain	200 mm/min	MPa	DIN 53504		5,5
C Compression set	24 h; 70 °C	%	DIN ISO 815-1, Method A		45
C Compression set	72 h; 23 °C	%	DIN ISO 815-1		22
C Compression set	24 h; 70 °C	%	DIN ISO 815-1, Method C		36
C Abrasion resistance		mm ³	ISO 4649 method A		69
Rebound resilience		%	ISO 4662		63
Tear strength	500 mm/min	kN/m	ISO 34-1		39
Thermal properties					
Tensile storage modulus	-20 °C	MPa	ISO 6721-1,-4		125
Tensile storage modulus	20 °C	MPa	ISO 6721-1,-4		11
Tensile storage modulus	60 °C	MPa	ISO 6721-1,-4		9
Other properties (23 °C)					
C Density		kg/m ³	ISO 1183-1		1060
Recommended Processing and Drying Conditions					
Injection molding-Melt temperature		°C	-	190 - 210	
Injection molding-Mold temperature		°C	-		20 - 40
Extrusion-Melt temperature		°C	-	175 - 210	
Maximum drying temperature		°C	-		80

C These property characteristics are taken from the CAMPUS plastics data bank and are based on the international catalogue of basic data for plastics according to ISO 10350.

Impact properties: N = non-break, P = partial break, C = complete break



Desmopan 9370AU

Disclaimer

Covestro AG
Business Unit Polyurethanes
Kaiser-Wilhelm-Allee 60
51373 Leverkusen
Germany
www.TPU.covestro.com
www.covestro.com

Page 2 of 2 pages

Edition 05.02.2016

 **Desmopan®**

ISO Datasheet