

Arnitel[®] EE8100

TPC-ET

Injection Molding

Print Date: 2016-09-26

Properties	Typical Data	Unit	Test Method
Rheological properties			
Melt volume-flow rate	100	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Mechanical properties			
Shore A Hardness (15s)	67	-	ISO 868
Tensile modulus	9.5	MPa	ISO 527-1/-2
Stress at break	13.5	MPa	ISO 527-1/-2
Nominal strain at break	940	%	ISO 527-1/-2
Other properties			
Density	1060	kg/m ³	ISO 1183

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.

