

TECHNYL[®] BLUE

TECHNYL[®] A 218 V30 BLACK 34NG

TECHNICAL DATA SHEET

Revised: August, 2017

TECHNYL[®] A 218 V30 Black 34 NG is a polyamide 66, reinforced with 30% of glass fiber, heat stabilized, for injection moulding. This grade has been specially designed to improve its resistance to automotive cooling liquids, increasing lifetime of parts in permanent contact with such liquids.

GENERAL

| | | |
|---------------------------|--|---|
| Material Status | • Commercial: Active | |
| Availability | • Africa & Middle East • Asia Pacific • Europe | • Latin America • North America |
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight | |
| Additive | • Heat Stabilizer | |
| Key Benefits | • Good Flow • Glycol Resistance • Heat Aging Resistance | • Heat Stabilized (Inorganic) • Hydrolysis Resistant • Good Mold Release |
| Applications | • Automotive applications • Coolant pipes • Cooling connectors • Expansion tanks | • Oil filter modules • Radiator end tanks • Thermostat housings • Water pumps |
| Certification/Compliance | • EC 1907/2006 (REACH) • EN 45545 | • UL QMFZ2 |
| RoHS Compliance | • RoHS Compliant | |
| Automotive Specifications | • CHRYSLER MS-DB-41 CPN4018 Color: Black • FORD WSK-M4D752-A • GM GMW16270P-PA66-GF30 • GM GMW3038P-PA66-GF30H • GM GMW3038P-PA66-GF30H Color: Black | • GM GMW3038P-PA66-GF30J • GM GMW3038P-PA66-GF30J Color: Black • IMDS ID 29006804 • RENAULT PMR 2017 AS 26 |
| Colors Available | • Black | |
| Forms | • Pellets | |
| Processing Method | • Injection Molding | |
| Resin ID (ISO 1043) | • PA66-GF30 | |

PROPERTIES

Typical values of properties are for Black grades

| Physical | Dry | Conditioned Unit | Test Method |
|---------------------------|------|------------------|-------------|
| Molding Shrinkage | | | ISO 294-4 |
| Across Flow | 1.1 | % | |
| Flow | 0.40 | % | |
| Water Absorption | | | ISO 62 |
| 24 hr, 23°C | 0.80 | % | |
| Equilibrium, 23°C, 50% RH | 1.7 | % | |

Solvay Engineering Plastics

www.solvay.com - www.technyl.com

Tel: 00 800 55 400 600

technyl-emea@solvay.com - Europe, Middle East, Africa

technyl-apac@solvay.com - Asia Pacific

technyl-americas@solvay.com - Americas

Page: 1 of 6



SOLVAY

asking more from chemistry[®]

| Physical | Dry | Conditioned | Unit | Test Method |
|---------------------------------------|------------|--------------------|-------------------|--------------------|
| Density | 1.36 | | g/cm ³ | ISO 1183/A |
| Mechanical | | | | |
| | Dry | Conditioned | Unit | Test Method |
| Tensile Modulus (23°C) | 10000 | 7500 | MPa | ISO 527-2/1A |
| Tensile Stress (Break, 23°C) | 190 | 135 | MPa | ISO 527-2/1A |
| Tensile Elongation | | | | |
| Break, 23°C | 3.0 | | % | ASTM D638 |
| Break, 23°C | 3.0 | 7.0 | % | ISO 527-2 |
| Flexural Modulus | | | | |
| 23°C | 9000 | | MPa | ASTM D790 |
| 23°C | 9000 | 6400 | MPa | ISO 178 |
| Flexural Strength | | | | |
| 23°C | 290 | | MPa | ASTM D790 |
| 23°C | 280 | 185 | MPa | ISO 178 |
| Charpy Notched Impact Strength (23°C) | 11 | 15 | kJ/m ² | ISO 179/1eA |
| Charpy Unnotched Impact Strength | | | | |
| 23°C | 75 | 88 | kJ/m ² | ISO 179/1eU |
| 23°C | 70 | | kJ/m ² | ISO 179/1fU |
| Notched Izod Impact | | | | |
| 23°C | 120 | | J/m | ASTM D256 |
| 23°C | 10 | 18 | kJ/m ² | ISO 180 |
| Thermal | | | | |
| | Dry | Conditioned | Unit | Test Method |
| Deflection Temperature Under Load | | | | |
| 1.8 MPa, Unannealed | 255 | | °C | ASTM D648 |
| 1.8 MPa, Unannealed | 250 | | °C | ISO 75-2/1Af |
| Melting Temperature | 262 | | °C | ISO 11357-3 |
| Electrical | | | | |
| | Dry | Conditioned | Unit | Test Method |
| Surface Resistivity | 6.0E+14 | 1.0E+12 | ohms | IEC 60093 |
| Volume Resistivity | 1.0E+15 | 1.0E+13 | ohms·cm | IEC 60093 |
| Electric Strength (2.00 mm) | 34 | 29 | kV/mm | IEC 60243-1 |
| Relative Permittivity | 3.70 | 4.00 | | IEC 60250 |
| Dissipation Factor | 0.010 | 0.11 | | IEC 60250 |
| Comparative Tracking Index | | | | IEC 60112 |
| Solution A | 600 | 600 | V | |
| Solution B | 500 | | V | |
| Flammability | | | | |
| | Dry | Conditioned | Unit | Test Method |
| Flame Rating | | | | UL 94 |
| 0.8 mm | HB | | | |
| 1.6 mm | HB | | | |
| 3.2 mm | HB | | | |

| Flammability | Dry | Conditioned Unit | Test Method |
|---------------------------------------|------------|-------------------------|--------------------|
| Glow Wire Flammability Index (1.6 mm) | 650 | °C | IEC 60695-2-12 |
| Oxygen Index | 23 | % | ISO 4589-2 |

PROCESSING

| Injection | Dry Unit |
|------------------------|-----------------|
| Drying Temperature | 80 °C |
| Suggested Max Moisture | 0.15 % |
| Rear Temperature | 270 to 280 °C |
| Middle Temperature | 275 to 285 °C |
| Front Temperature | 280 to 290 °C |
| Mold Temperature | 70 to 100 °C |

Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h

Injection Advice:

- For reinforced polyamides, Solvay recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design

DISCLAIMER

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitutive for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and Solvay is at their disposal to supply any additional information.

SAFETY INFORMATION

Detailed information regarding safety are available on the safety data sheet (SDS). SDS is sent with the first material order or available by contacting our customer services

REGULATIONS COMPLIANCE

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with ROHS Directive 2011/65/EU and 2015/863 as amended.

Grades produced or imported in Europe comply with REACH directive 1907/2006/EC as amended.

CUSTOMER SERVICES


Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design


You can find more information on Solvay Product range on our internet product finder at the following address:
<http://www.technyl.com>

MULTIPOINT DATA

Isothermal Stress vs. Strain (ISO 11403-1)



Viscosity vs. Shear Rate (ISO 11403-2)



Notes

Typical properties: these are not to be construed as specifications.